

CREPE PAPER

Crepe paper is primarily used for wrapping irregular shapes and surfaces which cannot be achieved with flat/presspaper.

HIGHLIGHTS

- Sustainable and environmentally friendly solution for plastic replacement
- High degree of strength and purity

KEY FEATURES & BENEFITS

- Made from 100% unbleached sulphate (kraft) wood pulp
- Widths available from 20mm – 2500mm and grammage from 42/60 gsm – 100/200 gsm
- Pinhole-free paper with enhanced mechanical properties
- Natural brown color

APPLICATIONS

- Packaging
- Filter paper
- Industrial applications e.g. filters, joint tape, surface protection, insulation & vibration dampening, and more



Crepe Paper

STANDARD SIZES

Grammage	Standard widths	Standard roll diameters	
		Internal Ø	Outside Ø
42/60, 60/90, 100/200 g/m ²	1500, 1250, 1000, 750 mm	Ø 70 mm	Ø 550* mm (Sea) Ø 590 mm (Truck)
ALU FOIL 90/135 g/m ²	730 mm	Ø 70 mm	Ø 550* mm (Sea) Ø 590 mm (Truck) Ø 750 mm

*Other sizes available by request

AVAILABLE PRODUCT CHARACTERISTICS

Grammage	42/60, 60/90, 100/200 g/m ²
Standard type	Standard specification*
	Unbleached

*additional parameters on request

TECHNICAL DATA

Property Unit		Paper ID							
		42/60 g/m ² CF110		60/90 g/m ² CFS00		100/200 g/m ² CFS80		90/135 g/m ² CA000	
		Min	Max	Min	Max	Min	Max	Min	Max
Thickness	mm	0.22	0.25	0.26	0.32	0.50	0.60	0.34	0.42
Grammage	g/m ²	60.0	66.0	85.0	95.0	190.0	210.0	130.0	140.0
Extended tensile index									
MD	Nm/g ²	33.0	-	33.0	-	33.0	-	33.0	-
CMD	Nm/g ²	20.0	-	20.0	-	20.0	-	20.0	-
Width related breaking load									
MD	kN/m	2.5	-	3.0	-	4.5	-	4.0	-
CMD	kN/m	1.5	-	2.0	-	4.5	-	3.0	-
Breaking length									
MD	km	3.0	-	2.5	-	1.5	-	2.0	-
CMD	km	2.5	-	2.0	-	2.0	-	2.0	-
Elongation at break									
MD	%	45	55	45	55	90	110	45	60
CMD	%	4.0	-	3.0	-	3.0	-	2.0	-
Water content (conditioned 23/50)	%	-	8.0	-	8.0	-	8.0	-	8.0
pH value of aqueous extract		-	0.5	-	1.0	-	1.0	-	35.0
Coating		-	-	-	-	-	-	Aluminium foil laminated	

MD = Machine Direction
CMD = Cross Machine Direction

Rev. 06.24

Weidmann CSM
Rapperswil, Switzerland
T +41 55 221 41 11

Weidmann CSM
St. Johnsbury VT, USA
T +1 802 748 8106

Weidmann CSM
Shanghai, China
T +86 21 3463 7680

www.weidmann-csm.com | csm@weidmann-group.com